

LOGO FIX 530

Product Description

LOGO FIX 530 is a double sided Tissue Tape with a modified solvent acrylic adhesive. The tape has a good adhesion and holding power. It can be applied to various surfaces.

Applications

Suitable for gloss / matt paper and non-woven surfaces.
For general nameplate adhesion.

Technical description	Technical values
Adhesive	Modified Solvent Acrylic
Carrier	Black Tissue
Total Thickness without liner	0,100 mm (+/- 0,010)
Liner	105 g white PE-coated paper
Initial Tack FINAT 9	> 12 N / 25 mm
Peel Adhesion FINAT 1	> 13 N / 25 mm
Holding Power FINAT 8	> 24 Hours
Temperature Rang long term short term	- 0°C - + 70°C - 20°C - + 100°C

Features at a glance			
Initial tack	good	Metal	excellent
Peel adhesion	good	High energy plastics PVC, ABS ...	good
Holding power (Shear)	good	Low energy plastics PE, PP ...	not good
Adhesion on		Foam	good
- even surfaces	excellent	Rubber	not good
- rough surfaces	good	Fabric	good
Surface conformity	good	Paper / Cardboards	excellent
Aging resistance	good	Glass / Ceramics	excellent

The prohibited substances according to the RoHS directive (2002/95/EC) and 2006/122/EG (PFOS) are not included in this product.

APPLICATION

Temperature: between +15°C and +30°C. Surface must be clean and free from dust and grease. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

STORAGE & SHELF LIFE

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

NOTE

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using our product that it is suitable for the material for your intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale.