

LOGO-TRANS 315

Product Description

LOGO TRANS 315 is ideal for bonding materials with glossy coatings where an aggressive adhesive with high initial adhesion is desired.

Technical description	Technical values
Adhesive	Solvent Acrylic with Glass Fibres
Carrier	-
Thickness	0,13 mm
Liner	Honey Silicone Paper
Peel Adhesion (PSTC 1)	28 +/- 3 N / 25 mm
Temperature Range	- 40°C - + 120°C

LOGO TRANS 315 is reverse wound on 1"-core for use with ATG hand dispenser available as follows:

- 6 mm x 16,5 mtr. => 144 rolls / carton
- 9 mm x 16,5 mtr. => 96 rolls / carton
- 12 mm x 16,5 mtr. => 72 rolls / carton
- 19 mm x 16,5 mtr. => 48 rolls / carton

The roll length of 33 mtr. is available on request.

The prohibited substances according to the RoHS directive (2002/95/EC) and 2006/122/EG (PFOS) are not included in this product.

APPLICATION

Temperature: between +15°C and +30°C. Surface must be clean and free from dust and grease. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

STORAGE & SHELF LIFE

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

NOTE

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using our product that it is suitable for the material for your intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale.