

# LOGO-FIX 330

## Product Description

LOGO FIX 330 consists of a thin polyester film coated on one side with a removable acrylic adhesive and on the other side with a permanent rubber based adhesive.

## Characteristics

<i>Adhesion with substrates</i>			
Metal/Aluminium	Low / Medium	Textile/Cotton	Low / Medium
Glass/Ceramics	Low / Medium	Rubber/EPDM	Low / Medium
Painted surface	Low / Medium	Acrylic/PET	Low / Medium
Wood/Board/Paper	Low / Medium	Polystyrene	Low / Medium
Soft PVC	Low / Low	PP/PE/PS	Low / Medium
Rigid PVC	Low / Medium	Smooth substrate	Low / Medium
PC/ABS	Low / Medium	Rough substrate	Medium / Medium

## Resistance

Resistant to water, detergents and alcohol, Plasticizers: side 1 is highly resistant whereas side 2 has low resistance, Outdoor: side 1 is highly resistant and side 2 has low resistance. Not recommended for use in contact with aliphatic or aromatic hydrocarbons.

Technical description	Technical values
Adhesive	removable Acrylic / permanent Hotmelt
Carrier	PET-Film, transparent
Thickness	0,07 mm
Liner	White Silicone Paper
Peel Adhesion – FTM 1 (on V2A steel after 24 hours, 180° peel at 300 mm/min. and 23°)	permanent: > 15 N/25 mm removable: > 4 N/25 mm
Shear Adhesion – FTM 8 (25 mm <sup>2</sup> on V2A steel, 1 kg weight at 23° and 50 % rel. atmospheric humidity)	permanent: > 250 h removable: -
Temperature Range	- 40°C - + 90°C

The prohibited substances according to the RoHS directive (2002/95/EC) and 2006/122/EG (PFOS) are not included in this product.

## APPLICATION

Temperature: between +15°C and +30°C. Surface must be clean and free from dust and grease. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

## **STORAGE & SHELF LIFE**

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

## **NOTE**

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using our product that it is suitable for the material for your intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale.