

LOGO MOUNT 855

Product Description

LOGO-MOUNT 855 is a 200 kg / m³ black PE-Foam coated on both sides with a solvent acrylic adhesive.

- Strong adhesion and superb holding power.
- It has strong holding power on various surfaces, e.g. PVC, ABS, PC, steel, aluminium, etc.
- It has very good durability, which is resistant to moisture, UV and temperature changes.
- The foam material act as a gentle shock absorbent.

Applications

Mounting and bonding of various substrates, such as:

Small ornamental displays, bathroom mirrors, automobile emblems and nameplates.

Technical description	Technical values
Adhesive	Modified Solvent Acrylic
Carrier Density	200 kg / m ³ black PE-Foam
Carrier Thickness	0,50 mm
Total Thickness without liner	~ 0,63 mm
Liner	White PE-coated paper
Initial Tack FINAT 9	≥ 16 N / 25 mm
Peel Adhesion FINAT 1	≥ 20 N / 25 mm
Holding Power FINAT 8	≥ 500 Hours
Temperature Rang long term short term	- 20°C - + 80°C - 40°C - + 150°C

The prohibited substances according to the RoHS directive (2002/95/EC) and 2006/122/EG (PFOS) are not included in this product.

APPLICATION

Temperature: between +15°C and +30°C. Surface must be clean and free from dust and grease. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

STORAGE & SHELF LIFE

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

NOTE

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using our product that it is suitable for the material for your intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale.