

LOGO-MOUNT 870

Product Description

LOGO MOUNT 870 is a double sided mounting adhesive tape with closed cell polyethylene co-polymeric foam carrier. The acrylic adhesive guarantees for excellent final adhesion and resistance to heat and aging and in combination with the compressible foam carrier results additionally in a high initial adhesion to rough and slightly uneven material surfaces. Furthermore special mention must be made to the excellent resistance to UV and solvents as well as its good weathering properties.

This adhesive tape is used for attaching decorative and functional strips, lettering, emblems, covers, holders and extruded rubber profiles in the automotive industry.

Technical description	Technical values
Adhesive	Solvent Acrylic
Carrier	Black PE-Foam, 180 kg/m ³
Thickness	0,8 mm
Liner	White Silicone Paper
Peel Adhesion (on V2A steel after 20 min., 180° peel at 300 mm/min. and 23°)	> 10 N / 25 mm
Shear Adhesion (25 mm ² on V2A steel, 1 kg weight at 23° and 50 % rel. atmospheric humidity)	> 200 Hours
Temperature Range	- 40°C - + 120°C

The prohibited substances according to the RoHS directive (2002/95/EC) and 2006/122/EG (PFOS) are not included in this product.

APPLICATION

Temperature: between +15°C and +30°C. Surface must be clean and free from dust and grease. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24 hours at 23°C.

STORAGE & SHELF LIFE

Clean and dry in a well ventilated area, preferably at a temperature between 10°C and 30°C. Stored under these conditions shelf life will be a minimum of one year.

NOTE

All data above mentioned and technical information given above are typical values, gained from tests we believe to be reliable. Please ensure before using our product that it is suitable for the material for your intended application. For technical assistance please call our product specialists. The data and statements are intended as a source of information, are given without guarantee and do not constitute a warranty. They can vary according to the application conditions. All materials described herein are subject to our conditions of sale.